

| TECHNICAL DATA (Typical Values)          |   |
|--|---|
| Complies with the following standards:   |   |
|  |   |
| PRODUCT IDENTITY                         |   |
| Туре:                                    | powder  |
| Color:                                   | Grey  |
| Bulk Density (kg/m³):                    | 1300  |
| Dry Solid Content (%):                   | 100   |
| EMICODE:                                 | EC1 Plus - very low emission                          |
| APPLICATION DATA (at +23°C and 50% R.H.) |   |
| Mixing ratio:                            | 100 parts Floorowall with 23-25 parts water by weight |
| Consistency of mix:                      | pasty   |
| Density of the mix (kg/m³):              | 1,400   |
| pH of mix:                               | Over 12   |
| Pot life:                                | 6-8 hours   |
| Application temperature range:           | from +5°C to +35°C                                    |
| Open time (acc. EN 1346):                | > 20 minutes  |
| Adjustability time:                      | approx. 45 minutes                                    |
| Ready for grouting on walls:             | after 3-6 hours                                       |
| Ready for grouting on floors:            | after 24 hours  |
| Set to light foot traffic:               | 24 hours  |
| Ready for use:                           | 14 days   |
| FINAL PERFORMANCES                       |   |
| Bonding strength according to EN 1348    |   |
| (N/mm²):                                 |   |
| – initial bonding after 28 days: 1.0     | 1.0   |
| - adhesion after heating:0.60 0.60       | 0.60  |
| – Adhesion after water immersion:0.80    | 0.80  |
| – bonding after freeze/thaw cycles: 0.90 | 0.90  |
| Resistance to damp:                      | excellent   |
|  |   |

excellent

excellent

from -30°C to +90°C

Resistance to ageing:

Resistance to solvents and oils:

Resistance to temperature :